



# FICHA TÉCNICA

## PAPEL KRAFT MG MARRON (LISO / VERJURADO)

Características	Unidad	60	70	75	90	
GRAMAJE	g/m <sup>2</sup>	60	70	75	90	ISO-536
ESPEJOR	Micras	80	92	92	111	ISO-534
BULK (MANO)	Cm <sup>3</sup> /g	1.33	1.31	1,23	1.23	ISO-534
TEST COBB 60 (seg)	g/m <sup>2</sup>	26	26	26	27	ISO-535 IQT 14020
PERMEABILIDAD BENDTSEN	Cm <sup>3</sup> /mn	240	250	250	200	ISO 5636/3
BRILLO	%	24	22	22	23	TAPPI 480
TRACCION MD	m	10900	10600	10400	10100	ISO 1924/2
TRACCION CD	m	5500	5100	4900	4700	ISO 1924/2
ELONGACION MD	%	1.5	1.6	1.5	1.5	ISO 1924/2
ELONGACION CD	%	3.4	3.5	3.4	3.6	ISO 1924/2
INDICE RASGADO MD	nM.m <sup>2</sup> /g	7.7	7.9	7.5	11.5	NFQ03011
INDICE RASGADO CD	nM.m <sup>2</sup> /g	9.0	9.3	9.1	12.5	NFQ03011
INDICE ESTALLIDO	k.Pa.m <sup>2</sup> /g	4.2	4.1	4.2	4.2	ISO 2758
RUGOSIDAD BENDTSEN	Cm <sup>3</sup> /mn	120	150	150	200	ISO 2494
HUMEDAD	%	6.5	6.5	6.5	6.5	ISO 287

### CARACTERÍSTICAS:

- ✓ Conforme a la Norma : NFQ 15008
- ✓ Adecuado para uso alimentario
- ✓ Tolerancia: Peso Medio : + / - 3%
- ✓ PEFC 100 % Certificado